

可生產製品規範表 Product Specifications

品名 Product Name		熱浸鍍 55% 鋁-鋅鋼捲 ( 鋁鋅龍 ) Hot-dip 55%Al-Zn coated steel coil (PhuizerLume)															
規格 Specifications		CNS 15237 2013			JIS G 3321 2017			ASTM A792M 2010			AS 1397 2011			EN10346 2015			
		SGLCD SGLCDD	SGLCC	SGLC340 SGLC400 SGLC440 SGLC490 SGLC540 SGLC570	SGLCD SGLCDD	SGLCC	SGLC400 440 570	CS Type A B C FS	DS	SS Grade 230 255 275 340 550	G3	G1 G2	G250 G300 G350 G450 G500 G550	DX51D	DX52D DX53D	S220GD S250GD S280GD S320GD S350GD	S550GD
底材厚度 (mm) Base Steel Thickness (mm)	燐輝 Yieh Phui	0.3   1.5	0.16   2.0	0.2   2.0	0.3   1.5	0.16   2.0	0.20   2.0	0.16   2.0	0.30   1.5	0.20   2.0	0.3   1.5	0.16   2.0	0.2   2.0	0.16   2.0	0.3   1.5	0.20   2.0	0.20   2.0
	燐輝 Yieh Phui (China)	--	--	--	SGLCC, SGLC340: 0.17~2.02mm; SGLCD1~3: 0.3~1.4mm; SGLC400: 0.2~1.5mm; SGLC440: 0.2~2.0mm; SGLC570: 0.17~2.0mm			CS Type A, B, C, Grade 230, 255: 0.17~2.02mm; FS Type A, B: 0.295~1.6mm; DS: 0.3~1.4mm; SS Grade 275: 0.22~1.5mm; SS Grade 340: 0.2~2.0mm; SS Grade 550: 0.17~2.0mm			G1, G250: 0.17~2.02mm; G300: 0.28~1.5mm; G350: 0.2~2.0mm; G450: 0.6~1.5mm; G500, G550: 0.17~2.0mm			DX51D, S220GD, S250GD: 0.17~2.02mm; DX52D: 0.295~1.6mm; DX53D, 54D: 0.3~1.4mm; S280GD: 0.22~1.5mm; S320GD, S350GD: 0.2~2.0mm; S550GD: 0.17~2.0mm			
鍍層量 Coating Mass	一般鋅花 Regular Spangle	AZ70 AZ90 AZ100 AZ120 AZ150 AZ170 AZ185			AZ70 AZ90 AZ120 AZ150 AZ170 AZ185			AZM100 AZM110 AZM120 AZM150 AZM165 AZM180			AZ150			AZ 100 AZ 150 AZ 185			
表面精整 Surface Finish	一般鍍 55% 鋁-鋅鋅花 Regular Spangle																
表面處理 Surface Treatment	鉻酸、塗油、有機樹脂 (耐指紋塗膜) 或環保有機樹脂 (環保耐指紋塗膜) 處理 Chromating, Oiled, Resin Coated (Anti-Fingerprint), or Green Treatment (Environmentally Friendly Anti-Fingerprint)																
備註 Remarks	<p>1. 厚度、寬度、平坦度……等之公差容許範圍，依各製品規範之要求。</p> <p>2. 對各種表面精整厚度 2.0mm 以下，可再實施調質處理。</p> <p>3. 鋼捲內徑為 508 或 610mm；外徑之最大容許值為 2000mm。</p> <p>4. 不在上述範圍之產品，如尺寸、鍍層、規格等，請以個案詢問專案開發方式進行。經客我協商後，燐輝亦可提供國際規範以外之鍍層量。</p> <p>1. Tolerance for thickness, width, flatness and so on conforms to individual product specification.</p> <p>2. All products with thickness 2.0mm and under can be skinpassed.</p> <p>3. Coil inside diameters can be either 508mm or 610mm. Maximum coil outside diameter is 2000mm.</p> <p>4. Please make inquires to our sales division for products with special specifications. Coating mass beyond the specifications above can be provided by YP upon mutual agreement between customer and us.</p>																